

YDEEVNEDEKLARATION

DoP nr.: MKT-451 - da

♦ Varetypens unikke identifikationskode: Injektionssystem VM-EA

♦ Tilsigtet anvendelse: Limede ankre til forankring i ikke-revnet beton,

se bilag / Annex B

♦ Fabrikant:
MKT Metall-Kunststoff-Technik GmbH & Co.KG

Auf dem Immel 2 67685 Weilerbach

♦ System eller systemer til vurdering og kontrol af konstansen af ydeevnen:

1

♦ Europæisk vurderingsdokument:

EAD 330499-01-0601 ETA-16/0898, 25.04.2020

Europæisk teknisk vurdering:

Teknisk vurderingsorgan:

TZÚS, Prag

Notificeret organ/notificerede organer:

NB 1343 – MPA, Darmstadt

♦ Deklareret ydeevne/deklarerede ydeevner:

Væsentlige funktioner	Ydeevne					
Mekanisk modstandsdygtighed og stabilitet (BWR 1)						
Karakteristiske modstande under trækbelastning (statiske og kvasistatiske effekter)	Bilag / Annex C1, C2, C4					
Karakteristiske modstande under tværgående stress (statiske og kvasistatiske effekter)	Bilag / Annex C1, C3, C5					
Forskydninger	Bilag / Annex C6					
Holdbarhed	Bilag / Annex B1					
Hygiejne, sundhed og miljø (BWR 3)						
Indhold, emission og / eller frigivelse af farlige stoffer	Ydeevne ikke bedømt					

Ydeevnen for den vare, der er anført ovenfor, er i overensstemmelse med den deklarerede ydeevne. Denne ydeevnedeklaration er udarbejdet i overensstemmelse med forordning (EU) nr. 305/2011 på eneansvar af den fabrikant, der er anført ovenfor.

Underskrevet for fabrikanten og på dennes vegne af:

Stefan Weustenhagen

(CEO)


Weilerbach, 25.04.2020

Dipl.-Ing. Detlef Bigalke (Leder af produktudvikling)




Originalen af denne erklæringserklæring blev skrevet på tysk. I tilfælde af afvigelser i oversættelsen er den tyske udgave gyldig.

Installation threaded rod M8 to M24



Installation internally threaded anchor rod VMU-IG M6 to M16



 t_{fix} = thickness of fixture

d_f = diameter of clearance hole in the fixture

hef = effective embedment depth


 h_0 = depth of drill hole

 h_{min} = minimum thickness of member

Injection System VM-EA for concrete	
Product description Installation conditions	Annex A1


Cartridge: VM-EA, VM-EA blue, VM-EA express, VM-EA low speed

150 ml, 280 ml, 300 ml up to 330 ml and 380 ml up to 420 ml cartridge (Type: coaxial)




Imprint: VM-EA, VM-EA blue, VM-EA express, VM-EA low speed, processing notes, charge-code, shelf life, hazard-code, storage temperature, curing- and processing time (depending on the temperature) optional: with travel scale

235 ml, 345 ml up to 360 ml and 825 ml cartridge (Type: "side-by-side")




165 ml and 300 ml cartridge (Type: "foil tube")



Imprint: VM-EA, VM-EA blue, VM-EA express, VM-EA low speed, processing notes, charge-code, shelf life, hazard-code, storage temperature, curing- and processing time (depending on the temperature) optional: with travel scale

Static mixer




Injection System VM-EA for concrete

Annex A2

Threaded rod

Threaded rod VMU-A, V-A with washer and hexagon nut M8, M10, M12, M16, M20, M24 (zinc plated, A4, HCR)



Threaded rod VM-A (material sold by the metre, to be cut at the required length) **M8, M10, M12, M16, M20, M24** (zinc plated, A2, A4, HCR)


Commercial standard threaded rod with:

M8, M10, M12, M16, M20, M24 (zinc plated, A2, A4, HCR)

- Materials, dimensions and mechanical properties see Table A1
- Inspection certificate 3.1 acc. to EN 10204:2004

Internally threaded anchor rod

VMU-IG M6, VMU-IG M8, VMU-IG M10, VMU-IG M12, VMU-IG M16 (zinc plated, A4, HCR)



Marking e.g.: $\langle 1 \rangle$ M8

Identifying mark of manufacturing plant

I Internal thread

M8 Size of internal thread A4 additional marking for

stainless steel

HCR additional marking for high

corrosion resistant steel

Product description

Threaded rod and internally threaded anchor rod

Annex A3

Table A1: Materials

Part	Designation		Material					
electro hot-di	galvanized	≥ 5 µm ≥ 45 µm ≥ 45 µm	acc. to EN ISO 4042:1999 or acc. to EN ISO 1461:2009, EN ISO 10684:2004+AC:2009 or acc. to EN ISO 17668:2016					
		Property class	characteristic steel ultimate strength	characteristic steel yield strength	fracture elongation	EN 40007.4000		
		4.6		f _{yk} ≥ 240 N/mm²;	A ₅ > 8 %	- EN 10087:1998, EN 10263:2001;		
1		4.8	f _{uk} ≥ 400 N/mm²	f _{yk} ≥ 320 N/mm²	A ₅ > 8 %	Commercial standard		
	Threaded rod	5.6	f _{uk} ≥ 500 N/mm²	f _{yk} ≥ 300 N/mm²	A ₅ > 8 %	threaded rod:		
		5.8	f _{uk} ≥ 500 N/mm²	f _{yk} ≥ 400 N/mm²	A ₅ > 8 %	EN ISO 898-1:2013		
		8.8	f _{uk} ≥ 800 N/mm²	f _{yk} ≥ 640 N/mm²	A ₅ > 8 %			
		4	for class 4.6 or 4.8	rods				
2	Hexagon nut	5	for class 4.6, 4.8, 5	5.6 or 5.8 rods		EN ISO 898-2:2012		
		8	for class 4.6, 4.8, 5	for class 4.6, 4.8, 5.6, 5.8 or 8.8 rods				
3	Washer		e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 or EN ISO 7094:2000					
4	Internally threaded	5.8	Steel, electroplated or sherardized A ₅ > 8%			EN 40007-4000		
4	anchor rod 8.8		Steel, electroplated	d or sherardized	A ₅ > 8%	EN 10087:1998		
Stain	less steel A2 ¹⁾ less steel A4 corrosion resistant s	steel HCR		07 / 1.4311 / 1.456 04 / 1.4571 / 1.457 65)				
		Property class	characteristic steel ultimate strength	characteristic steel yield strength	fracture elongation			
1	Threaded rod	50	f_{uk} = 500 N/mm ²	f_{yk} = 210 N/mm ²	A ₅ > 8 %	EN 10088-1:2014 - EN ISO 3506-1:2009		
		70	f_{uk} = 700 N/mm ²	f_{yk} = 450 N/mm ²	A ₅ > 8 %			
		80	f _{uk} = 800 N/mm ²	f _{yk} = 600 N/mm ²	A ₅ > 8 %			
		50	for class 50 rods					
2	Hexagon nut 70		for class 50 or 70	EN 10088-1:2014 EN ISO 3506-2:2009				
		80	for class 50,70 or					
3	Washer		e.g.: EN ISO 887 EN ISO 7093	:2006, EN ISO 708 3:2000 or EN ISO 7	9:2000, '094:2000	EN 10088-1:2014		
4	Internally threaded anchor rod	70	property class 70	EN 10088-1:2014				

¹⁾ For property classes 50 and 70

Injection System VM-EA for concrete	
Product description Materials	Annex A4

Specifications of intended use

Injection System	n VM-EA	Anchor rod	Internally threaded anchor rod			
Static or quasi-st	atic action	VMU-A, V-A, VM-A, commercial standard threaded rod M8 – M24 zinc plated, A2, A4, HCR	VMU-IG M6 - M16 electroplated or sherardized, A4, HCR			
		reinforced or unreinforced normal weight concrete acc. to EN 206:2013+A1:2016				
Base materials		strength classes acc. to EN 206:2013+A1:2016: C20/25 to C50/60				
		uncracked concrete				
Temperature Range I:	24°C / 40°C	Temperature range from -40°C to +40°C with max. long term temperature +24°C and max. short term temperature +40 °C				
Temperature Range II:	50°C / 80°C	Temperature range from -40°C to +80°C with max. long term temperature +50°C and max. short term temperature +80 °C				

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (all materials).
- For all other conditions according to EN 1993-1-4:2006+A1:2015 corresponding to corrosion resistance classes:
 - Stainless steel A2 according to Annex A, Table A3: CRC II
 - Stainless steel A4 according to Annex A, Table A3: CRC III
 - High corrosion resistant steel HCR according to Annex A, Table A3: CRC V

Steel grades of a higher corrosion resistance class may be used

Design:

- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position
 of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to
 supports, etc.)
- · Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work
- Anchorages are designed in accordance with EN 1992-4:2018 or TR 055.

Concrete condition:

- I1 = installation in dry or wet (water saturated) concrete and use in service in dry or wet concrete
- I2 = installation in water-filled drill holes (not sea water) and use in service in dry or wet concrete

Installation:

- · Hole drilling by hammer or compressed air drill mode
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site

Installation direction:

• D3 = downward and horizontal and upwards (e.g. overhead) installation

Injection System VM-EA for concrete	
Intended use Specifications	Annex B1

Table B1: Installation parameters for threaded rod

Threaded rod			M 8	M 10	M 12	M 16	M 20	M 24
Diameter of threaded rod	d=d _{nom}	[mm]	8	10	12	16	20	24
Nominal drill hole diameter	d_0	[mm]	10	12	14	18	24	28
Effective anchorage depth	$h_{\text{ef,min}}$	[mm]	60	60	70	80	90	96
Effective anchorage depth	h _{ef,max}	[mm]	160	200	240	320	400	480
Diameter of clearance hole in the fixture	d _f ≤	[mm]	9	12	14	18	22	26
Installation torque	T _{inst} ≤	[Nm]	10	20	40	80	120	160
Minimum thickness of member	h _{min}	[mm]	h _{ef} + 30 mm ≥ 100 mm			h _{ef} + 2d ₀		
Minimum spacing	Smin	[mm]	40	50	60	80	100	120
Minimum edge distance	Cmin	[mm]	40	50	60	80	100	120

Table B2: Installation parameters for internally threaded anchor rod


Internally threaded anchor rod			VMU-IG M 6	VMU-IG M 8	VMU-IG M 10	VMU-IG M 12	VMU-IG M 16
Inner diameter of threaded rod	d ₂	[mm]	6	8	10	12	16
Outer diameter of threaded rod ¹⁾	d=d _{nom}	[mm]	10	12	16	20	24
Nominal drill hole diameter	d_0	[mm]	12	14	18	24	28
Effective anabarage denth	h _{ef,min}	[mm]	60	70	80	90	96
Effective anchorage depth —	h _{ef,max}	[mm]	200	240	320	400	480
Diameter of clearance hole in the fixture ¹⁾	d _f ≤	[mm]	7	9	12	14	18
Installation torque	T _{inst} ≤	[Nm]	10	10	20	40	60
Minimum screw-in depth	lıg	[mm]	8	8	10	12	16
Minimum thickness of member	h _{min}	[mm]	h _{ef} + 30 mm ≥ 100 mm			h _{ef} + 2d ₀	
Minimum spacing	Smin	[mm]	50	60	80	100	120
Minimum edge distance	C _{min}	[mm]	50	60	80 100 120		

¹⁾ With metric thread acc. to EN 1993-1-8:2005+AC:2009

Injection System VM-EA for concrete	
Intended use Installation parameters	Annex B2

Installation instructions

Drilling of the hole



Drill with hammer drill a hole into the base material to the size required by the selected anchor (Table B1 or B2). In case of aborted drill hole, the drill hole shall be filled with mortar.

Cleaning

Attention! Standing water in the drill hole must be removed before cleaning!

<u>Cleaning with compressed air</u> (all diameters)



Starting from the bottom or back of the drill hole, blow out the hole with compressed air

(min. 6 bar) a minimum of four times.

If the drill hole ground is not reached, an extension must be used.

2b. min. 6 bar

Attach the brush to a drilling machine or a battery screwdriver. Brush the hole with an appropriate sized wire brush $> d_{b,min}$ (Table B3) a minimum of **four** times.


If the drill hole ground is not reached, a brush extension shall be used.

Finally blow the hole clean again with compressed air (min. 6 bar) a minimum of **four** times. If the drill hole ground is not reached an extension shall be used.

Manual cleaning

2.

Drill hole diameter $d_0 \le 20$ mm or drill hole depth $h_0 \le 240$ mm



Starting from the bottom or back of the drill hole, blow the hole clean with the blow-out pump minimum of **four** times. If the drill hole ground is not reached an extension shall be used.



Attach the brush to a drilling machine or a battery screwdriver. Brush the hole with an appropriate sized wire brush $> d_{b,min}$ (Table B3) a minimum of **four** times.

If the drill hole ground is not reached, a brush extension shall be used.

Finally blow the hole clean again with the blow-out pump a minimum of **four** times. If the drill hole ground is not reached an extension shall be used.

After cleaning, the drill hole has to be protected against re-contamination in an appropriate way, until dispensing the mortar in the drill hole. If necessary, the cleaning repeated has to be directly before dispensing the mortar. In-flowing water must not contaminate the drill hole again.

Injection System VM-EA for concrete

2c.

Installation instructions

Annex B3

Installation instructions (continuation)

	anation instructions	, (continuation)
Inje	ction	
3.	MIN INTERNATIONAL PROPERTY OF THE PROPERTY OF	Attach a supplied static-mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. For foil tube cartridges: cut off the foil tube clip before use. For every working interruption longer than the recommended working time (Table B4) as well as for new cartridges, a new static-mixer shall be used.
4.	hef	Prior to inserting the anchor rod into the filled drill hole, the position of the embedment depth shall be marked on the anchor rod.
5.	min.3x →	Prior to dispensing into the drill hole, squeeze out separately a minimum of three full strokes and discard non-uniformly mixed adhesive components until the mortar shows a consistent grey or blue (VM-EA blue) color. For foil tube cartridges discard a minimum of six full strokes.
6a.		Starting from the bottom or back of the cleaned drill hole fill the hole up to approximately two-thirds with adhesive. Slowly withdraw the static mixing nozzle as the hole fills to avoid air pockets. For embedment larger than 190mm an extension nozzle shall be used. Observe the gel-/ working times given in Table B4.
Inse	rting the anchor	
7.		Push the threaded rod into the hole while turning slightly to ensure proper distribution of the adhesive until the embedment depth is reached. The anchor shall be free of dirt, grease, oil or other foreign material.
8.		Make sure that the anchor is fully seated up to the full embedment depth and that excess mortar is visible at the top of the hole. If these requirements are not maintained, the application has to be renewed. For overhead installation, the anchor should be fixed (e.g. by wedges).
9.		Allow the adhesive to cure to the specified time prior to applying any load or torque. Do not move or load the anchor until it is fully cured (attend Table B4).
10.		Remove excess mortar.
11.	T _{inst}	The fixture can be mounted after curing time. Apply installation torque T _{inst} according to Table B1 or B2.

Injection System VM-EA for concrete	
Intended use Installation instructions (continuation)	Annex B4


Table B3: Parameter cleaning tools

Threaded rod	Internally threaded anchor rod	Drill bit - Ø	Brush - Ø	min. Brush - Ø
[-]	[-]	d₀ [mm]	d _b [mm]	d _{b,min} [mm]
M8	-	10	12	10,5
M10	VMU-IG M6	12	14	12,5
M12	VMU-IG M8	14	16	14,5
M16	VMU-IG M10	18	20	18,5
M20	VMU-IG M12	24	26	24,5
M24	VMU-IG M16	28	30	28,5

Recommended compressed air tool (min 6 bar) all applications

Blow-out pump (volume 750ml)

Drill bit diameter (d₀): 10 mm to 20 mm Drill hole depth (h₀): \leq 240 mm



Cleaning brush RB



Table B4: Working time and curing time

Concrete temperature	VM-EA low speed		VM-EA, VM-EA blue 1)		VM-EA express	
	working time	minimum curing time	working time	minimum curing time	working time	minimum curing time
-10 to -6°C	-	-	-	-	60 min	4 h
-5 to -1°C	-	-	90 min	6 h	45 min	2 h
0 to +4°C	-	-	45 min	3 h	25 min	80 min
+5 to +9°C	-	-	25 min	2 h	10 min	45 min
+10 to +14°C	30 min	5 h	20 min	100 min	4 min	25 min
+15 to +19°C	20 min	210 min	15 min	80 min	3 min	20 min
+20 to +29°C	15 min	145 min	6 min	45 min	2 min	15 min
+30 to +34°C	10 min	80 min	4 min	25 min	-	-
+35 to +39°C	6 min	45 min	2 min	20 min	-	-
+40 to +44°C	4 min	25 min	-	-	-	-
+45 °C	2 min	20 min	-	-	-	-
Cartridge temperature	+5°C to +45°C		+5°C to +40°C		0°C to +30°C	

¹⁾ The VM-EA blue injection mortar has a curing time proof by changing the color from blue to grey after minimum curing time. The curing time proof is only valid for the standard version of the mortar

Injection System VM-EA for concrete	
Intended Use Parameter cleaning tools, working time and curing time	Annex B5