

SUORITUSTASOILMOITUS

DoP Nro: **MKT-2.1-601**_fi


- ✧ **Tuotetyypin yksilöllinen tunniste:** **Ruiskutusjärjestelmä VMH betoniin**
- ✧ **Aiottu käyttötarkoitus
(aiotut käyttötarkoitukset):** Injektionestojärjestelmä ankkurointi betoniin,
katso liite / Annex B
- ✧ **Valmistaja:** MKT Metall-Kunststoff-Technik GmbH & Co.KG
Auf dem Immel 2
67685 Weilerbach
- ✧ **Rakennustuotteen suoritustason pysyvyyden
arviointi- ja varmennusjärjestelmä(t):** 1
- ✧ **Eurooppalainen arviointiasiakirja:** **EAD 330499-01-0601**
Eurooppalainen tekninen arviointi: **ETA-17/0716, 11.05.2021**
Teknisestä arvioinnista vastaava laitos: DIBt, Berlin
Ilmoitettu laitos/ilmoitetut laitokset: NB 2873 – Technische Universität Darmstadt


✧ **Ilmoitettu suoritustaso/ilmoitetut suoritustasot:**

| Olennaiset ominaisuudet | Suoritustaso |
|---|---|
| Mekaaninen lujuus ja vakaus (BWR 1) | |
| Ominaisresistanssit vetolujuudessa (staattiset ja lähes staattiset vaikutukset) | Liite / Annex B3, C1, C3, C4, C5, C8, C9, C11, C12 |
| Ominaisresistanssit poikittaisessa rasituksessa (staattiset ja lähes staattiset vaikutukset) | Liite / Annex C2, C6, C10, C13 |
| Vuorossa | Liite / Annex C15 – C17 |
| Ominaisvastus ja siirtymät seismiselle suorituskyluokalle C1 + C2 | Liite / Annex C7, C14, C15 |
| Hygienia, terveys ja ympäristö (BWR 3) | |
| Vaarallisten aineiden pitoisuus, päästöt ja / tai päästöt | Suorituskykyä ei arvioitu |

Edellä yksilöidyn tuotteen suoritustaso on ilmoitettujen suoritustasojen joukon mukainen. Tämä suoritustasoilmoitus on asetuksen (EU) N:o 305/2011 mukaisesti annettu edellä ilmoitetun valmistajan yksinomaisella vastuulla.

Valmistajan puolesta allekirjoittanut:


Stefan Weustenhagen
(Toimitusjohtaja)
Weilerbach, 11.05.2021

p.p. 
Dipl.-Ing. Detlef Bigalke
(Tuotekehityksen johtaja)



Tämän suoritusilmoituksen alkuperäinen teksti on kirjoitettu saksaksi. Jos käännökset poikkeavat toisistaan, saksankielinen versio on pätevä.

Specification of intended use

| Static and quasi-static action | working life 50 years | working life 100 years |
|---|---|---|
| Threaded rod Internally threaded anchor rod Rebar | M8 - M30 VMU-IG M6 - VMU-IG M20 Ø8 - Ø32 | |
| Base material | cracked or uncracked concrete | |
| | strength classes C20/25 to C50/60 compacted, reinforced or unreinforced normal weight concrete (without fibers) acc. to EN 206:2013+A1:2016 | |
| Hole drilling | hammer drilling / compressed air drilling / vacuum drilling | |
| Temperature range ¹⁾ | I: -40°C to +40°C II: -40°C to +80°C III: -40°C to +120°C IV: -40°C to +160°C | I: -40°C to +40°C II: -40°C to +80°C |

| Seismic action | performance category C1 | performance category C2 |
|---------------------------------|---|--|
| Threaded rod Rebar | M8 - M30 Ø8 - Ø32 | M12 - M24 --- |
| Base material | cracked or uncracked concrete | |
| | strength classes C20/25 to C50/60 compacted, reinforced or unreinforced normal weight concrete (without fibers) acc. to EN 206:2013+A1:2016 | |
| Hole drilling | hammer drilling / compressed air drilling / vacuum drilling | |
| Temperature range ¹⁾ | I: -40°C to +40°C II: -40°C to +80°C III: -40°C to +120°C IV: -40°C to +160°C | I: -40°C to +40°C II: -40°C to +80°C III: -40°C to +120°C IV: -40°C to +160°C |

¹⁾ Temperature Range I: max. long term temperature +24°C and max. short term temperature +40°C
 Temperature Range II: max. long term temperature +50°C and max. short term temperature +80°C
 Temperature Range III: max. long term temperature +72°C and max. short term temperature +120°C
 Temperature Range IV: max. long term temperature +100°C and max. short term temperature +160°C

Injection System VMH for concrete

Intended Use
Specifications

Annex B1

Specification of intended use

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions: all materials
- For all other conditions:
Intended use of Materials according to Annex A4, Table A1 corresponding corrosion resistance classes CRC according to EN 1993-1-4:2006+A1:2015

Design:

- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work
- Anchorages are designed in accordance with EN 1992-4:2018 and Technical Report TR 055, Edition February 2018

Installation:

- Dry or wet concrete or waterfilled drill holes (not seawater)
- Hole drilling by hammer or compressed air drill or vacuum drill mode
- Overhead installation allowed
- Anchor installation carried out by appropriately qualified personnel and under the responsibility of the person competent for technical matters on site
- The injection mortar is assessed for installation at minimum concrete temperature of -5°C, where subsequently the temperature in the concrete does not rise at a rapid rate, i.e. from the minimum installation temperature to 24°C within a 12-hour period.
- Internally threaded anchor rod: screws and threaded rods (incl. nut and washer) must at least correspond to the material and strength class of the internally threaded anchor rod used

Injection System VMH for concrete

Intended Use
Specifications

Annex B2

Table B1: Installation parameters for threaded rods

| Threaded rod | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|---|--|------|---|-----|--------------------------|-----------------|-----|-----|-----|-----|
| Diameter of threaded rod | $d=d_{nom}$ | [mm] | 8 | 10 | 12 | 16 | 20 | 24 | 27 | 30 |
| Nominal drill hole diameter | d_0 | [mm] | 10 | 12 | 14 | 18 | 22 | 28 | 30 | 35 |
| Effective anchorage depth | $h_{ef,min}$ | [mm] | 60 | 60 | 70 | 80 | 90 | 96 | 108 | 120 |
| | $h_{ef,max}$ | [mm] | 160 | 200 | 240 | 320 | 400 | 480 | 540 | 600 |
| Diameter of clearance hole in the fixture ²⁾ | Pre-setting installation $d_f \leq$ | [mm] | 9 | 12 | 14 | 18 | 22 | 26 | 30 | 33 |
| | Through setting installation $d_f \leq$ | [mm] | 12 | 14 | 16 | 20 | 24 | 30 | 33 | 40 |
| Maximum installation torque | $max.T_{inst} \leq$ | [Nm] | 10 | 20 | 40 (35) ¹⁾ | 60 | 100 | 170 | 250 | 300 |
| Minimum thickness of member | h_{min} | [mm] | $h_{ef} + 30 \text{ mm}$ $\geq 100 \text{ mm}$ | | | $h_{ef} + 2d_0$ | | | | |
| Minimum spacing | s_{min} | [mm] | 40 | 50 | 60 | 75 | 95 | 115 | 125 | 140 |
| Minimum edge distance | c_{min} | [mm] | 35 | 40 | 45 | 50 | 60 | 65 | 75 | 80 |

¹⁾ max. installation torque for M12 with steel grade 4.6

²⁾ for applications under seismic loading the diameter of clearance hole in the fixture shall be at maximum $d_{nom} + 1 \text{ mm}$ or alternatively the annular gap between fixture and threaded rod shall be completely filled with mortar

Table B2: Installation parameters for internally threaded anchor rods

| Internally threaded anchor rod | | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 |
|--|---------------------|------|---|--------|---------|-----------------|---------|---------|
| Inner diameter of threaded rod | d_2 | [mm] | 6 | 8 | 10 | 12 | 16 | 20 |
| Outer diameter of threaded rod ¹⁾ | $d=d_{nom}$ | [mm] | 10 | 12 | 16 | 20 | 24 | 30 |
| Nominal drill hole diameter | d_0 | [mm] | 12 | 14 | 18 | 22 | 28 | 35 |
| Effective anchorage depth | $h_{ef,min}$ | [mm] | 60 | 70 | 80 | 90 | 96 | 120 |
| | $h_{ef,max}$ | [mm] | 200 | 240 | 320 | 400 | 480 | 600 |
| Diameter of clearance hole in the fixture | $d_f \leq$ | [mm] | 7 | 9 | 12 | 14 | 18 | 22 |
| Maximum installation torque | $max.T_{inst} \leq$ | [Nm] | 10 | 10 | 20 | 40 | 60 | 100 |
| Minimum screw-in depth | l_{IG} | [mm] | 8 | 8 | 10 | 12 | 16 | 20 |
| Minimum thickness of member | h_{min} | [mm] | $h_{ef} + 30 \text{ mm}$ $\geq 100 \text{ mm}$ | | | $h_{ef} + 2d_0$ | | |
| Minimum spacing | s_{min} | [mm] | 50 | 60 | 75 | 95 | 115 | 140 |
| Minimum edge distance | c_{min} | [mm] | 40 | 45 | 50 | 60 | 65 | 80 |

¹⁾ with metric thread acc. to EN 1993-1-8:2005+AC:2009

Table B3: Installation parameters for rebar

| Rebar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 |
|---|--------------|------|---|---------|---------|-----------------|------|--------------|---------|---------|------|------|
| Diameter of rebar | $d=d_{nom}$ | [mm] | 8 | 10 | 12 | 14 | 16 | 20 | 24 | 25 | 28 | 32 |
| Nominal drill hole diameter ¹⁾ | d_0 | [mm] | 10 12 | 12 14 | 14 16 | 18 | 20 | 25 30 32 | 30 32 | 30 32 | 35 | 40 |
| Effective anchorage depth | $h_{ef,min}$ | [mm] | 60 | 60 | 70 | 75 | 80 | 90 | 96 | 100 | 112 | 128 |
| | $h_{ef,max}$ | [mm] | 160 | 200 | 240 | 280 | 320 | 400 | 480 | 500 | 560 | 640 |
| Minimum thickness of member | h_{min} | [mm] | $h_{ef} + 30 \text{ mm}$ $\geq 100 \text{ mm}$ | | | $h_{ef} + 2d_0$ | | | | | | |
| Minimum spacing | s_{min} | [mm] | 40 | 50 | 60 | 70 | 75 | 95 | 120 | 120 | 130 | 150 |
| Minimum edge distance | c_{min} | [mm] | 35 | 40 | 45 | 50 | 50 | 60 | 70 | 70 | 75 | 85 |

¹⁾ for diameter Ø8, Ø10, Ø12, Ø24 and Ø25 both nominal drill hole diameter can be used

Injection System VMH for concrete

Intended use
Installation parameters

Annex B3

Table B4: Parameter cleaning and setting tools







| Threaded rod | Internally threaded anchor rod | Rebar | Drill bit Ø | Brush Ø | min. Brush Ø |
|---|---|---|--|---|-------------------------|
|  |  |  |  |  | |
| [-] | [-] | Ø [mm] | d ₀ [mm] | d _b [mm] | d _{b,min} [mm] |
| M8 | | 8 | 10 | 11,5 | 10,5 |
| M10 | VMU-IG M 6 | 8 / 10 | 12 | 13,5 | 12,5 |
| M12 | VMU-IG M 8 | 10 / 12 | 14 | 15,5 | 14,5 |
| | | 12 | 16 | 17,5 | 16,5 |
| M16 | VMU-IG M10 | 14 | 18 | 20,0 | 18,5 |
| | | 16 | 20 | 22,0 | 20,5 |
| M20 | VMU-IG M12 | | 22 | 24,0 | 22,5 |
| | | 20 | 25 | 27,0 | 25,5 |
| M24 | VMU-IG M16 | | 28 | 30,0 | 28,5 |
| M27 | | 24 / 25 | 30 | 31,8 | 30,5 |
| | | 24 / 25 | 32 | 34,0 | 32,5 |
| M30 | VMU-IG M20 | 28 | 35 | 37,0 | 35,5 |
| | | 32 | 40 | 43,5 | 40,5 |

Table B5: Retaining washer

| Drill bit Ø |  | Installation direction and use | | |
|---------------------|---|--------------------------------|-------------------------|-----|
| d ₀ [mm] | [-] | ↓ | → | ↑ |
| 10 | No retaining washer required | | | |
| 12 | | | | |
| 14 | | | | |
| 16 | | | | |
| 18 | VM-IA 18 | h _{ef} > 250mm | h _{ef} > 250mm | all |
| 20 | VM-IA 20 | | | |
| 22 | VM-IA 22 | | | |
| 25 | VM-IA 25 | | | |
| 28 | VM-IA 28 | | | |
| 30 | VM-IA 30 | | | |
| 32 | VM-IA 32 | | | |
| 35 | VM-IA 35 | | | |
| 40 | VM-IA 40 | | | |



Vacuum drill bit

Drill bit diameter (d₀): all diameters
 Vacuum drill bit (MKT Hollow drill bit SB, Würth Saugbohrer or Heller Duster Expert) and a class M vacuum with minimum negative pressure of 253 hPa and a flow rate of minimum 42 l/s (150 m³/h)



Recommended compressed air tool (min 6 bar)

Drill bit diameter (d₀): all diameters



Blow-out pump (volume 750ml)

Drill bit diameter (d₀): 10 mm to 20 mm
 Drill hole depth (h₀): ≤ 10 d_{nom}
 for uncracked concrete

Injection System VMH for concrete


Intended Use
 Cleaning and setting tools

Annex B4

Installation Instructions

Drilling of the hole

1



Hammer drill or compressed air drill

Drill with hammer drill or compressed air drill a hole into the base material to the size required by the selected anchor (Table B1, B2 or B3). Continue with [step 2](#). In case of aborted drill hole, the drill hole shall be filled with mortar.

Vacuum drill bit: see Annex B4

Drill hole into the base material to the embedment size and embedment depth required by the selected anchor (Table B1, B2 or B3). This drilling system removes dust and cleans the drill hole during drilling. Continue with [step 3](#). In case of aborted hole, the drill hole shall be filled with mortar.


Cleaning (not applicable when using a vacuum drill)

Attention! Standing water in the drill hole must be removed before cleaning!

Cleaning with compressed air

all substrates and diameters according to Annex B1


2a



Starting from the bottom or back of the drill hole, blow out the hole with compressed air (min. 6 bar) a minimum of **two** times until return air stream is free of noticeable dust.

If the drill hole ground is not reached, an extension must be used.


2b



Check brush diameter (Table B4). Brush the hole with an appropriate sized wire brush $\geq d_{b,min}$ (Table B4) a minimum of **two** times.

If the drill hole ground is not reached with the brush, an appropriate brush extension must be used.

2c



Starting from the bottom or back of the drill hole, blow out the hole with compressed air (min. 6 bar) again a minimum of **two** times until return air stream is free of noticeable dust.


If the drill hole ground is not reached, an extension must be used.

2

Manual cleaning


uncracked concrete, dry and wet drill holes; drill hole diameter $d_0 \leq 20\text{mm}$ and drill hole depth $h_0 \leq 10 d_{nom}$

2a



Starting from the bottom or back of the drill hole, blow out the hole with the blow-out pump a minimum of **four** times until return air stream is free of noticeable dust.


2b



Check brush diameter (Table B4). Brush the hole with an appropriate sized wire brush $\geq d_{b,min}$ (Table B4) a minimum of **four** times.

If the drill hole ground is not reached with the brush, an appropriate brush extension must be used.

2c



Starting from the bottom or back of the drill hole blow out the hole again a minimum of **four** times until return air stream is free of noticeable dust.






After cleaning, the drill hole has to be protected against re-contamination in an appropriate way, until dispensing the mortar in the drill hole. If necessary, the cleaning has to be repeated directly before dispensing the mortar. In-flowing water must not contaminate the drill hole again.

Injection System VMH for concrete

Intended Use
Installation instructions

Annex B5

Installation instructions (continuation)

| Injection | | |
|-----------|--|--|
| 3 |  | Attach the supplied static-mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. For every working interruption longer than the recommended working time (Table B6) as well as for new cartridges, a new static-mixer shall be used. |
| 4 |  | Prior to inserting the rod into the filled drill hole, the position of the embedment depth shall be marked on the threaded rod or rebar |
| 5 |  | Prior to dispensing into the drill hole, squeeze out separately a minimum of three full strokes and discard non-uniformly mixed adhesive components until the mortar shows a consistent grey colour. |
| 6a |  | Starting from the bottom or back of the cleaned drill hole fill the hole up to approximately two-thirds with adhesive. Slowly withdraw the static mixing nozzle as the hole fills to avoid air pockets. If the drill hole ground is not reached, an appropriate extension nozzle shall be used. Observe working times given in Table B6. |
| 6b |  | Retaining washer and mixer nozzle extensions shall be used according to Table B5 for the following applications: <ul style="list-style-type: none"> • Horizontal installation (horizontal direction) and ground installation (vertical downwards direction): Drill bit-$\varnothing d_0 \geq 18$ mm and anchorage depth $h_{ef} > 250$mm • Overhead installation: Drill bit-$\varnothing d_0 \geq 18$ mm |

Injection System VMH for concrete

Intended Use
Installation instructions (continuation)

Annex B6

Installation instructions (continuation)

| Setting the fastening element | | |
|-------------------------------|--|--|
| 7 | | <p>Push the fastening element into the hole while turning slightly to ensure proper distribution of the adhesive until the embedment depth is reached.</p> <p>The anchor shall be free of dirt, grease, oil or other foreign material.</p> |
| 8 | | <p>After installation, the annular gap between anchor rod and concrete must be completely filled with mortar, in the case of push-through installation also in the fixture. If these requirements are not fulfilled, repeat application before end of working time!</p> <p>For overhead installation, the anchor should be fixed (e.g. by wedges).</p> |
| 9 | | <p>Allow the adhesive to cure to the specified time prior to applying any load or torque. Do not move or load the anchor until it is fully cured (attend Table B6).</p> |
| 10 | | <p>Remove excess mortar.</p> |
| 11 | | <p>The fixture can be mounted after curing time. Apply installation torque $\leq T_{inst}$ according to Table B1 or B2.</p> |
| 12 | | <p>In case of pre-setting installation, the annular gap between anchor rod and fixture may optionally be filled with mortar. Therefore, replace regular washer by washer with bore and plug on reducing adapter on static mixer. Annular gap is completely filled, when excess mortar seeps out.</p> |

Table B6: Working time and curing time

| Concrete temperature | Working time | Minimum curing time | |
|------------------------------|------------------------|---------------------|--------------|
| | | dry concrete | wet concrete |
| -5°C to -1°C | 50 min | 5 h | 10 h |
| 0°C to +4°C | 25 min | 3,5 h | 7 h |
| +5°C to +9°C | 15 min | 2 h | 4 h |
| +10°C to +14°C | 10 min | 1 h | 2 h |
| +15°C to +19°C | 6 min | 40 min | 80 min |
| +20°C to +29°C | 3 min | 30 min | 60 min |
| +30°C to +40°C | 2 min | 30 min | 60 min |
| Cartridge temperature | + 5°C to + 40°C | | |

Injection System VMH for concrete

Intended Use
Installation instructions (continuation) / Working and curing time

Annex B7

Table C1: Characteristic steel resistance for threaded rods under tension load

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|---|-------------------------------------|-----------------|------|------------|------------|------|-----|-----|-----|-----------------|-----------------|
| Steel failure | | | | | | | | | | | |
| Cross sectional area A_s [mm ²] | | | | 36,6 | 58,0 | 84,3 | 157 | 245 | 353 | 459 | 561 |
| Characteristic resistance under tension load ¹⁾ | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 and 4.8 | $N_{Rk,s}$ | [kN] | 15 (13) | 23 (21) | 34 | 63 | 98 | 141 | 184 | 224 |
| | Property class 5.6 and 5.8 | $N_{Rk,s}$ | [kN] | 18 (17) | 29 (27) | 42 | 78 | 122 | 176 | 230 | 280 |
| | Property class 8.8 | $N_{Rk,s}$ | [kN] | 29 (27) | 46 (43) | 67 | 125 | 196 | 282 | 368 | 449 |
| Stainless steel | A2, A4 and HCR Property class 50 | $N_{Rk,s}$ | [kN] | 18 | 29 | 42 | 79 | 123 | 177 | 230 | 281 |
| | A2, A4 and HCR Property class 70 | $N_{Rk,s}$ | [kN] | 26 | 41 | 59 | 110 | 171 | 247 | _ ³⁾ | _ ³⁾ |
| | A4 and HCR Property class 80 | $N_{Rk,s}$ | [kN] | 29 | 46 | 67 | 126 | 196 | 282 | _ ³⁾ | _ ³⁾ |
| Partial factor ²⁾ | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 | $\gamma_{Ms,N}$ | [-] | 2,0 | | | | | | | |
| | Property class 4.8 | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| | Property class 5.6 | $\gamma_{Ms,N}$ | [-] | 2,0 | | | | | | | |
| | Property class 5.8 | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| | Property class 8.8 | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| Stainless steel | A2, A4 and HCR Property class 50 | $\gamma_{Ms,N}$ | [-] | 2,86 | | | | | | | |
| | A2, A4 and HCR Property class 70 | $\gamma_{Ms,N}$ | [-] | 1,87 | | | | | | _ ³⁾ | _ ³⁾ |
| | A4 and HCR Property class 80 | $\gamma_{Ms,N}$ | [-] | 1,6 | | | | | | _ ³⁾ | _ ³⁾ |

¹⁾ the characteristic resistances apply for all anchor rods with the cross sectional area A_s specified here: VMU-A, V-A, VM-A. For commercial standard threaded rods with a smaller cross sectional area (e.g. hot-dip galvanized threaded rods M8, M10 according to EN ISO 10684:2004 + AC:2009), the values in brackets are valid.

²⁾ in absence of other national regulations

³⁾ Anchor type not part of the ETA

Injection System VMH for concrete

Performance
Characteristic values for **threaded rods** under **tension loads**

Annex C1

Table C2: Characteristic steel resistance for threaded rods under shear load

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|---|-----------------------------------|---------------------|------------|------------|------|------|-----|-----|------------------|------------------|-----|
| Steel failure | | | | | | | | | | | |
| Cross sectional area A_s [mm ²] | | | | 36,6 | 58,0 | 84,3 | 157 | 245 | 353 | 459 | 561 |
| Characteristic resistances under shear load¹⁾ | | | | | | | | | | | |
| Steel failure <u>without</u> lever arm | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 and 4.8 | $V^{0}_{Rk,s}$ [kN] | 9 (8) | 14 (13) | 20 | 38 | 59 | 85 | 110 | 135 | |
| | Property class 5.6 and 5.8 | $V^{0}_{Rk,s}$ [kN] | 11 (10) | 17 (16) | 25 | 47 | 74 | 106 | 138 | 168 | |
| | Property class 8.8 | $V^{0}_{Rk,s}$ [kN] | 15 (13) | 23 (21) | 34 | 63 | 98 | 141 | 184 | 224 | |
| Stainless steel | A2, A4 and HCR, property class 50 | $V^{0}_{Rk,s}$ [kN] | 9 | 15 | 21 | 39 | 61 | 88 | 115 | 140 | |
| | A2, A4 and HCR, property class 70 | $V^{0}_{Rk,s}$ [kN] | 13 | 20 | 30 | 55 | 86 | 124 | .. ³⁾ | .. ³⁾ | |
| | A4 and HCR, property class 80 | $V^{0}_{Rk,s}$ [kN] | 15 | 23 | 34 | 63 | 98 | 141 | .. ³⁾ | .. ³⁾ | |
| Steel failure <u>with</u> lever arm | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 and 4.8 | $M^{0}_{Rk,s}$ [Nm] | 15 (13) | 30 (27) | 52 | 133 | 260 | 449 | 666 | 900 | |
| | Property class 5.6 and 5.8 | $M^{0}_{Rk,s}$ [Nm] | 19 (16) | 37 (33) | 65 | 166 | 324 | 560 | 833 | 1123 | |
| | Property class 8.8 | $M^{0}_{Rk,s}$ [Nm] | 30 (26) | 60 (53) | 105 | 266 | 519 | 896 | 1333 | 1797 | |
| Stainless steel | A2, A4 and HCR, property class 50 | $M^{0}_{Rk,s}$ [Nm] | 19 | 37 | 66 | 167 | 325 | 561 | 832 | 1125 | |
| | A2, A4 and HCR, property class 70 | $M^{0}_{Rk,s}$ [Nm] | 26 | 52 | 92 | 232 | 454 | 784 | .. ³⁾ | .. ³⁾ | |
| | A4 and HCR, property class 80 | $M^{0}_{Rk,s}$ [Nm] | 30 | 59 | 105 | 266 | 519 | 896 | .. ³⁾ | .. ³⁾ | |
| Partial factor ²⁾ | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 | $\gamma_{Ms,V}$ [-] | 1,67 | | | | | | | | |
| | Property class 4.8 | $\gamma_{Ms,V}$ [-] | 1,25 | | | | | | | | |
| | Property class 5.6 | $\gamma_{Ms,V}$ [-] | 1,67 | | | | | | | | |
| | Property class 5.8 | $\gamma_{Ms,V}$ [-] | 1,25 | | | | | | | | |
| | Property class 8.8 | $\gamma_{Ms,V}$ [-] | 1,25 | | | | | | | | |
| Stainless steel | A2, A4 and HCR, property class 50 | $\gamma_{Ms,V}$ [-] | 2,38 | | | | | | | | |
| | A2, A4 and HCR, property class 70 | $\gamma_{Ms,V}$ [-] | 1,56 | | | | | | .. ³⁾ | .. ³⁾ | |
| | A4 and HCR, property class 80 | $\gamma_{Ms,V}$ [-] | 1,33 | | | | | | .. ³⁾ | .. ³⁾ | |

¹⁾ the characteristic resistances apply for all anchor rods with the cross sectional area A_s specified here: VMU-A, V-A, VM-A.
For commercial standard threaded rods with a smaller cross sectional area (e.g. hot-dip galvanized threaded rods M8, M10 according to EN ISO 10684:2004 + AC:2009), the values in brackets are valid

²⁾ in absence of other national regulations

³⁾ Anchor type not part of the ETA

Injection System VMH for concrete

Performance
Characteristic values for **threaded rods** under **shear loads**

Annex C2

Table C3: Characteristic values of concrete cone failure and splitting failure

| Threaded rods / Internally threaded anchor rods / Rebars | | | all sizes | |
|--|------------------------|---------------|-----------|-------------------------------------|
| Concrete cone failure | | | | |
| Factor k_1 | uncracked concrete | $k_{ucr,N}$ | [-] | 11,0 |
| | cracked concrete | $k_{cr,N}$ | [-] | 7,7 |
| Edge distance | | $c_{cr,N}$ | [mm] | $1,5 \cdot h_{ef}$ |
| Spacing | | $s_{cr,N}$ | [mm] | $2,0 \cdot c_{cr,N}$ |
| Splitting failure | | | | |
| Characteristic resistance | | $N^0_{Rk,sp}$ | [kN] | $\min (N_{Rk,p} ; N^0_{Rk,c})$ |
| Edge distance | $h/h_{ef} \geq 2,0$ | $c_{cr,sp}$ | [mm] | $1,0 \cdot h_{ef}$ |
| | $2,0 > h/h_{ef} > 1,3$ | | | $2 \cdot h_{ef} (2,5 - h / h_{ef})$ |
| | $h/h_{ef} \leq 1,3$ | | | $2,4 \cdot h_{ef}$ |
| Spacing | | $s_{cr,sp}$ | [mm] | $2,0 \cdot c_{cr,sp}$ |

Injection System VMH for concrete

Performance
 Characteristic values of **concrete cone failure** and **splitting failure**

Annex C3

Table C4: Characteristic values of tension loads for threaded rods, static and quasi-static action, working life 50 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|---|-------------------------|-----------------|-----------------|---------------------------------------|------|-------------------------|-----|-----|-----|-----|-----|-----|
| Steel failure | | | | | | | | | | | | |
| Characteristic resistance | | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}$ or see Table C1 | | | | | | | | |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | see Table C1 | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | |
| Temperature range | I | 40°C / 24°C | $\tau_{Rk,ucr}$ | [N/mm ²] | 17 | 17 | 16 | 15 | 14 | 13 | 13 | 13 |
| | II | 80°C / 50°C | | | 17 | 17 | 16 | 15 | 14 | 13 | 13 | 13 |
| | III | 120°C / 72°C | | | 15 | 14 | 14 | 13 | 12 | 12 | 11 | 11 |
| | VI | 160°C / 100°C | | | 12 | 11 | 11 | 10 | 9,5 | 9,0 | 9,0 | 9,0 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | |
| Temperature range | I | 40°C / 24°C | $\tau_{Rk,cr}$ | [N/mm ²] | 7,0 | 7,5 | 8,0 | 9,0 | 8,5 | 7,0 | 7,0 | 7,0 |
| | II | 80°C / 50°C | | | 7,0 | 7,5 | 8,0 | 9,0 | 8,5 | 7,0 | 7,0 | 7,0 |
| | III | 120°C / 72°C | | | 6,0 | 6,5 | 7,0 | 7,5 | 7,0 | 6,0 | 6,0 | 6,0 |
| | VI | 160°C / 100°C | | | 5,5 | 5,5 | 6,0 | 6,5 | 6,0 | 5,5 | 5,5 | 5,5 |
| Reduction factor ψ^0_{sus} in concrete C20/25 | | | | | | | | | | | | |
| Temperature range | I | 40°C / 24°C | ψ^0_{sus} | [-] | 0,90 | | | | | | | |
| | II | 80°C / 50°C | | | 0,87 | | | | | | | |
| | III | 120°C / 72°C | | | 0,75 | | | | | | | |
| | VI | 160°C / 100°C | | | 0,66 | | | | | | | |
| Increasing factors for concrete | | | ψ_c | C25/30 | 1,02 | | | | | | | |
| | | | | C30/37 | 1,04 | | | | | | | |
| | | | | C35/45 | 1,07 | | | | | | | |
| | | | | C40/50 | 1,08 | | | | | | | |
| | | | | C45/55 | 1,09 | | | | | | | |
| | | | | C50/60 | 1,10 | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | |
| Splitting failure | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | |
| Installation factor | | | | | | | | | | | | |
| dry or wet concrete | vacuum cleaning | | γ_{inst} | [-] | 1,2 | | | | | | | |
| | manual cleaning | | | | 1,2 | No performance assessed | | | | | | |
| | compressed air cleaning | | | | 1,0 | | | | | | | |
| water filled drill hole | compressed air cleaning | | γ_{inst} | [-] | 1,4 | | | | | | | |

Injection System VMH for concrete

Performance

Characteristic values of **tension loads** for **threaded rods**, working life **50 years**

Annex C4

Table C5: Characteristic values of tension loads for threaded rods, static and quasi-static action, working life 100 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|---|-------------------------|-----------------|---------------------|---------------------------------------|------|-----|-----|-------------------------|-----|-----|-----|-----|
| Steel failure | | | | | | | | | | | | |
| Characteristic resistance | | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}$ or see Table C1 | | | | | | | | |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | see Table C1 | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | |
| Temperature range | I | 40°C / 24°C | $\tau_{Rk,ucr,100}$ | [N/mm ²] | 17 | 17 | 16 | 15 | 14 | 13 | 13 | 13 |
| | II | 80°C / 50°C | | | 17 | 17 | 16 | 15 | 14 | 13 | 13 | 13 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | |
| Temperature range | I | 40°C / 24°C | $\tau_{Rk,cr,100}$ | [N/mm ²] | 5,5 | 6,0 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 |
| | II | 80°C / 50°C | | | 5,5 | 6,0 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 |
| Increasing factors for concrete | | | ψ_c | C25/30 | 1,02 | | | | | | | |
| | | | | C30/37 | 1,04 | | | | | | | |
| | | | | C35/45 | 1,07 | | | | | | | |
| | | | | C40/50 | 1,08 | | | | | | | |
| | | | | C45/55 | 1,09 | | | | | | | |
| | | | | C50/60 | 1,10 | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | |
| Splitting failure | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | |
| Installation factor | | | | | | | | | | | | |
| dry or wet concrete | vacuum cleaning | γ_{inst} | [-] | 1,2 | | | | | | | | |
| | manual cleaning | | | 1,2 | | | | No performance assessed | | | | |
| | compressed air cleaning | | | 1,0 | | | | | | | | |
| water filled drill hole | compressed air cleaning | γ_{inst} | [-] | 1,4 | | | | | | | | |

Injection System VMH for concrete

Performance

Characteristic values of **tension loads** for **threaded rods**, working life **100 years**

Annex C5

Table C6: Characteristic values of shear loads for threaded rods, static and quasi-static action

| Threaded rod | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|--|-----------------|--------------------|--|-----|-----|-----|-----|-----|----------------------------|------|--|
| Steel failure <u>without</u> lever arm | | | | | | | | | | | |
| Characteristic resistance Steel, zinc plated Class 4.6, 4.8, 5.6 and 5.8 | $V_{Rk,s}^0$ | [kN] | 0,6 · A_s · f_{uk} or see Table C2 | | | | | | | | |
| Characteristic resistance Steel, zinc plated, class 8.8, stainless steel A2, A4 and HCR | $V_{Rk,s}^0$ | [kN] | 0,5 · A_s · f_{uk} or see Table C2 | | | | | | | | |
| Ductility factor | k_7 | [-] | 1,0 | | | | | | | | |
| Partial factor | $\gamma_{Ms,V}$ | [-] | see Table C2 | | | | | | | | |
| Steel failure <u>with</u> lever arm | | | | | | | | | | | |
| Characteristic bending resistance | $M_{Rk,s}^0$ | [Nm] | 1,2 · W_{el} · f_{uk} or see Table C2 | | | | | | | | |
| Elastic section modulus | W_{el} | [mm ³] | 31 | 62 | 109 | 277 | 541 | 935 | 1387 | 1874 | |
| Partial factor | $\gamma_{Ms,V}$ | [-] | see Table C2 | | | | | | | | |
| Concrete pry-out failure | | | | | | | | | | | |
| Pry-out factor | k_8 | [-] | 2,0 | | | | | | | | |
| Concrete edge failure | | | | | | | | | | | |
| Effective length of anchor | l_f | [mm] | min (h_{ef} ; 12 d_{nom}) | | | | | | min (h_{ef} ; 300mm) | | |
| Outside diameter of anchor | d_{nom} | [mm] | 8 | 10 | 12 | 16 | 20 | 24 | 27 | 30 | |
| Installation factor | γ_{inst} | [-] | 1,0 | | | | | | | | |

Injection System VMH for concrete

Performance
Characteristic values of **shear loads** for **threaded rods**

Annex C6

Table C7: Characteristic values of tension loads for threaded rods, seismic action (performance category C1 + C2), working life 50 and 100 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|--|-------------------------|----------------------|----------------------|----------------------|-----|-----|-----|-----|-----------------|----------------------|-----|
| Steel failure | | | | | | | | | | | |
| Characteristic resistance | | $N_{Rk,s,C1}$ | [kN] | $1,0 \cdot N_{Rk,s}$ | | | | | | | |
| | | $N_{Rk,s,C2}$ | [kN] | - ¹⁾ | | | | | | $1,0 \cdot N_{Rk,s}$ | |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | see Table C1 | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | |
| Characteristic bond resistance in concrete C20/25 to C50/60 | | | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | $\tau_{Rk,C1}$ | [N/mm ²] | 7,0 | 7,5 | 8,0 | 9,0 | 8,5 | 7,0 | 7,0 | 7,0 |
| | | $\tau_{Rk,C2}$ | [N/mm ²] | - ¹⁾ | | 3,6 | 3,5 | 3,3 | 2,3 | - ¹⁾ | |
| | II: 80°C / 50°C | $\tau_{Rk,C1}$ | [N/mm ²] | 7,0 | 7,5 | 8,0 | 9,0 | 8,5 | 7,0 | 7,0 | 7,0 |
| | | $\tau_{Rk,C2}$ | [N/mm ²] | - ¹⁾ | | 3,6 | 3,5 | 3,3 | 2,3 | - ¹⁾ | |
| | III: 120°C / 72°C | $\tau_{Rk,C1}$ | [N/mm ²] | 6,0 | 6,5 | 7,0 | 7,5 | 7,0 | 6,0 | 6,0 | 6,0 |
| | | $\tau_{Rk,C2}$ | [N/mm ²] | - ¹⁾ | | 3,1 | 3,0 | 2,8 | 2,0 | - ¹⁾ | |
| VI: 160°C / 100°C | $\tau_{Rk,C1}$ | [N/mm ²] | 5,5 | 5,5 | 6,0 | 6,5 | 6,0 | 5,5 | 5,5 | 5,5 | |
| | $\tau_{Rk,C2}$ | [N/mm ²] | - ¹⁾ | | 2,5 | 2,7 | 2,5 | 1,8 | - ¹⁾ | | |
| Installation factor | | | | | | | | | | | |
| Compressed air cleaning | dry or wet concrete | γ_{inst} | [-] | 1,0 | | | | | | | |
| | water filled drill hole | | | 1,4 | | | | | | | |
| Vacuum cleaning | dry or wet concrete | γ_{inst} | [-] | 1,2 | | | | | | | |

¹⁾ No performance assessed

Table C8: Characteristic values of shear loads for threaded rods, seismic action (performance category C1 + C2)

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|---|--|-----------------|------|------------------------|-----|-----|-----|-----|-----|------------------------|-----|
| Steel failure <u>without</u> lever arm | | | | | | | | | | | |
| Characteristic resistance | | $V_{Rk,s,C1}$ | [kN] | $0,7 \cdot V^0_{Rk,s}$ | | | | | | | |
| | | $V_{Rk,s,C2}$ | [kN] | - ¹⁾ | | | | | | $0,7 \cdot V^0_{Rk,s}$ | |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | see Table C2 | | | | | | | |
| Factor for anchorages | without hole clearance | α_{gap} | [-] | 1,0 | | | | | | | |
| | with hole clearance between fastener and fixture | α_{gap} | [-] | 0,5 | | | | | | | |

¹⁾ No performance assessed

Injection System VMH for concrete

Performance
Characteristic values for **threaded rods** under **seismic action**

Annex C7

Table C9: Characteristic values of tension loads for internally threaded anchor rod, static and quasi-static action, working life 50 years

| Internally threaded anchor rod | | | | VMU-IG M6 | VMU-IG M8 | VMU-IG M10 | VMU-IG M12 | VMU-IG M16 | VMU-IG M20 |
|--|-------------------------|-----------------|----------------------|--------------|-------------------------|---------------|---------------|---------------|-------------------|
| Steel failure ¹⁾ | | | | | | | | | |
| Characteristic resistance, steel, zinc plated, property class | 5.8 | $N_{Rk,s}$ | [kN] | 10 | 17 | 29 | 42 | 76 | 123 |
| | 8.8 | $N_{Rk,s}$ | [kN] | 16 | 27 | 46 | 67 | 121 | 196 |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | |
| Characteristic resistance, stainless steel A4 / HCR, property class | 70 | $N_{Rk,s}$ | [kN] | 14 | 26 | 41 | 59 | 110 | 124 ²⁾ |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,87 | | | | | 2,86 |
| Combined pull-out and concrete failure | | | | | | | | | |
| Characteristic bond resistance in uncracked concrete C20/25 | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | $\tau_{Rk,ucr}$ | [N/mm ²] | 17 | 16 | 15 | 14 | 13 | 13 |
| | II: 80°C / 50°C | | | 17 | 16 | 15 | 14 | 13 | 13 |
| | III: 120°C / 72°C | | | 14 | 14 | 13 | 12 | 12 | 11 |
| | VI: 160°C / 100°C | | | 11 | 11 | 10 | 9,5 | 9,0 | 9,0 |
| Characteristic bond resistance in cracked concrete C20/25 | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | $\tau_{Rk,cr}$ | [N/mm ²] | 7,5 | 8,0 | 9,0 | 8,5 | 7,0 | 7,0 |
| | II: 80°C / 50°C | | | 7,5 | 8,0 | 9,0 | 8,5 | 7,0 | 7,0 |
| | III: 120°C / 72°C | | | 6,5 | 7,0 | 7,5 | 7,0 | 6,0 | 6,0 |
| | VI: 160°C / 100°C | | | 5,5 | 6,0 | 6,5 | 6,0 | 5,5 | 5,5 |
| Reduction factor ψ_{sus}^0 in concrete C20/25 | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | ψ_{sus}^0 | [-] | 0,90 | | | | | |
| | II: 80°C / 50°C | | | 0,87 | | | | | |
| | III: 120°C / 72°C | | | 0,75 | | | | | |
| | VI: 160°C / 100°C | | | 0,66 | | | | | |
| Increasing factors for concrete | | ψ_c | [-] | C25/30 | 1,02 | | | | |
| | | | | C30/37 | 1,04 | | | | |
| | | | | C35/45 | 1,07 | | | | |
| | | | | C40/50 | 1,08 | | | | |
| | | | | C45/55 | 1,09 | | | | |
| | | | | C50/60 | 1,10 | | | | |
| Concrete cone failure | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | |
| Splitting failure | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | |
| Installation factor | | | | | | | | | |
| dry or wet concrete | vacuum cleaning | γ_{inst} | [-] | 1,2 | | | | | |
| | manual cleaning | | | 1,2 | No performance assessed | | | | |
| | compressed air cleaning | | | 1,0 | | | | | |
| waterfilled drill hole | compressed air cleaning | γ_{inst} | [-] | 1,2 | | | | | |

¹⁾ fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod. The characteristic tension resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element

²⁾ for VMU-IG M20: property class 50

Injection System VMH for concrete

Performance

Characteristic values of **tension loads** for **internally threaded anchor rod**, working life **50 years**

Annex C8

Table C10: Characteristic values of tension loads for internally threaded anchor rod, static and quasi-static action, working life 100 years

| Internally threaded anchor rod | | | | VMU-IG M6 | VMU-IG M8 | VMU-IG M10 | VMU-IG M12 | VMU-IG M16 | VMU-IG M20 |
|---|-------------------------|---------------------|----------------------|--------------|-------------------------|---------------|---------------|---------------|-------------------|
| Steel failure ¹⁾ | | | | | | | | | |
| Characteristic resistance, steel, zinc plated, property class | 5.8 | $N_{Rk,s}$ | [kN] | 10 | 17 | 29 | 42 | 76 | 123 |
| | 8.8 | $N_{Rk,s}$ | [kN] | 16 | 27 | 46 | 67 | 121 | 196 |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | |
| Characteristic resistance, stainless steel A4 / HCR, property class | 70 | $N_{Rk,s}$ | [kN] | 14 | 26 | 41 | 59 | 110 | 124 ²⁾ |
| | | $\gamma_{Ms,N}$ | [-] | 1,87 | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | $\tau_{Rk,ucr,100}$ | [N/mm ²] | 17 | 16 | 15 | 14 | 13 | 13 |
| | II: 80°C / 50°C | | | 17 | 16 | 15 | 14 | 13 | 13 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | $\tau_{Rk,cr,100}$ | [N/mm ²] | 6,0 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 |
| | II: 80°C / 50°C | | | 6,0 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 |
| Increasing factors for concrete | | ψ_c | | C25/30 | 1,02 | | | | |
| | | | | C30/37 | 1,04 | | | | |
| | | | | C35/45 | 1,07 | | | | |
| | | | | C40/50 | 1,08 | | | | |
| | | | | C45/55 | 1,09 | | | | |
| | | | | C50/60 | 1,10 | | | | |
| Concrete cone failure | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | |
| Splitting failure | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | |
| Installation factor | | | | | | | | | |
| dry or wet concrete | vacuum cleaning | γ_{inst} | [-] | 1,2 | | | | | |
| | manual cleaning | | | 1,2 | No performance assessed | | | | |
| | compressed air cleaning | | | 1,0 | | | | | |
| waterfilled drill hole | compressed air cleaning | γ_{inst} | [-] | 1,2 | | | | | |

¹⁾ fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod. The characteristic tension resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element

²⁾ for VMU-IG M20: property class 50

Injection System VMH for concrete

Performance

Characteristic values of **tension loads** for **internally threaded anchor rod**, working life **100 years**

Annex C9

Table C11: Characteristic values of shear loads for internally threaded anchor rod, static and quasi-static action

| Internally threaded anchor rod | | | | VMU-IG M6 | VMU-IG M8 | VMU-IG M10 | VMU-IG M12 | VMU-IG M16 | VMU-IG M20 | |
|---|-----------------------------------|--------------------|-----------------|-----------|---------------------------------|------------|------------|------------|------------|-------------------------|
| Steel failure <u>without</u> lever arm ¹⁾ | | | | | | | | | | |
| Steel, zinc plated | Characteristic resistance | property class 5.8 | $V^0_{Rk,s}$ | [kN] | 6 | 10 | 17 | 25 | 45 | 74 |
| | Characteristic resistance | property class 8.8 | $V^0_{Rk,s}$ | [kN] | 8 | 14 | 23 | 34 | 60 | 98 |
| | Partial factor | | $\gamma_{Ms,V}$ | [-] | | 1,25 | | | | |
| Stainless steel | Characteristic resistance | property class 70 | $V^0_{Rk,s}$ | [kN] | 7 | 13 | 20 | 30 | 55 | 62 ²⁾ |
| | Partial factor | | $\gamma_{Ms,V}$ | [-] | | 1,56 | | | | 2,38 |
| Ductility factor | | | k_7 | [-] | | 1,0 | | | | |
| Steel failure <u>with</u> lever arm ¹⁾ | | | | | | | | | | |
| Steel, zinc plated | Characteristic bending resistance | property class 5.8 | $M^0_{Rk,s}$ | [Nm] | 8 | 19 | 37 | 66 | 167 | 325 |
| | Characteristic bending resistance | property class 8.8 | $M^0_{Rk,s}$ | [Nm] | 12 | 30 | 60 | 105 | 267 | 519 |
| | Partial factor | | $\gamma_{Ms,V}$ | [-] | | 1,25 | | | | |
| Stainless steel | Characteristic bending resistance | property class 70 | $M^0_{Rk,s}$ | [Nm] | 11 | 26 | 53 | 92 | 234 | 643 ²⁾ |
| | Partial factor | | $\gamma_{Ms,V}$ | [-] | | 1,56 | | | | 2,38 |
| Concrete pry-out failure | | | | | | | | | | |
| Pry-out factor | | | k_8 | [-] | | 2,0 | | | | |
| Concrete edge failure | | | | | | | | | | |
| Effective length of anchor | | | l_f | [mm] | min (h_{ef} ; 12 d_{nom}) | | | | | min (h_{ef} ; 300mm) |
| Outside diameter of anchor | | | d_{nom} | [mm] | 10 | 12 | 16 | 20 | 24 | 30 |
| Installation factor | | | γ_{inst} | [-] | | 1,0 | | | | |

¹⁾ fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod (exception: VMU-IG M20). The characteristic shear resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element

²⁾ for VMU-IG M20: Internally threaded rod: property class 50;
Fastening screws or threaded rods (incl. nut and washer): property class 70

Injection System VMH for concrete

Performance
Characteristic values of **shear loads** for **internally threaded anchor rod**

Annex C10

Table C12: Characteristic values of tension loads for rebar, static and quasi-static action, 50 years working life

| Reinforcing bar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | |
|---|-------------------------|--------------------|-------------------------|------|-------------------------|------|------|------|------|------|------|------|-----|
| Steel failure | | | | | | | | | | | | | |
| Characteristic resistance | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | |
| Cross sectional area | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | |
| Partial factor | $\gamma_{Ms,N}$ | [-] | 1,4 ²⁾ | | | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | $\tau_{Rk,ucr}$ | [N/mm ²] | 14 | 14 | 14 | 14 | 13 | 13 | 13 | 13 | 13 | 13 |
| | II: 80°C / 50°C | | | 14 | 14 | 14 | 14 | 13 | 13 | 13 | 13 | 13 | 13 |
| | III: 120°C / 72°C | | | 13 | 12 | 12 | 12 | 12 | 11 | 11 | 11 | 11 | 11 |
| | VI: 160°C / 100°C | | | 9,5 | 9,5 | 9,5 | 9,0 | 9,0 | 9,0 | 9,0 | 9,0 | 8,5 | 8,5 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | $\tau_{Rk,cr}$ | [N/mm ²] | 5,5 | 5,5 | 6,0 | 6,5 | 6,5 | 6,5 | 6,5 | 7,0 | 7,0 | 7,0 |
| | II: 80°C / 50°C | | | 5,5 | 5,5 | 6,0 | 6,5 | 6,5 | 6,5 | 6,5 | 7,0 | 7,0 | 7,0 |
| | III: 120°C / 72°C | | | 4,5 | 5,0 | 5,0 | 5,5 | 5,5 | 5,5 | 5,5 | 6,0 | 6,0 | 6,0 |
| | VI: 160°C / 100°C | | | 4,0 | 4,5 | 4,5 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 |
| Reduction factor ψ_{sus}^0 in concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | ψ_{sus}^0 | [-] | 0,90 | | | | | | | | | |
| | II: 80°C / 50°C | | | 0,87 | | | | | | | | | |
| | III: 120°C / 72°C | | | 0,75 | | | | | | | | | |
| | VI: 160°C / 100°C | | | 0,66 | | | | | | | | | |
| Increasing factor for concrete | ψ_c | [-] | C25/30 | 1,02 | | | | | | | | | |
| | | | C30/37 | 1,04 | | | | | | | | | |
| | | | C35/45 | 1,07 | | | | | | | | | |
| | | | C40/50 | 1,08 | | | | | | | | | |
| | | | C45/55 | 1,09 | | | | | | | | | |
| | | | C50/60 | 1,10 | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | |
| Relevant parameter | | | see Table C3 | | | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | |
| Relevant parameter | | | see Table C3 | | | | | | | | | | |
| Installation factor | | | | | | | | | | | | | |
| dry or wet concrete | vacuum cleaning | γ_{inst} | [-] | 1,2 | | | | | | | | | |
| | manual cleaning | | | 1,2 | No performance assessed | | | | | | | | |
| | compressed air cleaning | | | 1,0 | | | | | | | | | |
| waterfilled drill hole | compressed air cleaning | γ_{inst} | [-] | 1,4 | | | | | | | | | |

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

Injection System VMH for concrete

Performance

Characteristic values of tension loads for rebar, 50 years working life

Annex C11

Table C13: Characteristic values of tension loads for rebar, static and quasi-static action, 100 years working life

| Reinforcing bar | | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | |
|---|-------------------------|-----------------|---------------------|-------------------------|------|------|------|------|------|-------------------------|------|------|------|-----|
| Steel failure | | | | | | | | | | | | | | |
| Characteristic resistance | | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | |
| Cross sectional area | | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,4 ²⁾ | | | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | | | |
| Temperature range | I: | 40°C / 24°C | $\tau_{Rk,ucr,100}$ | [N/mm ²] | 14 | 14 | 14 | 14 | 13 | 13 | 13 | 13 | 13 | 13 |
| | II: | 80°C / 50°C | | | 14 | 14 | 14 | 14 | 13 | 13 | 13 | 13 | 13 | 13 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | | | |
| Temperature range | I: | 40°C / 24°C | $\tau_{Rk,cr,100}$ | [N/mm ²] | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,0 | 4,0 | 4,0 | 4,0 | 4,0 |
| | II: | 80°C / 50°C | | | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,0 | 4,0 | 4,0 | 4,0 | 4,0 |
| Increasing factor for concrete | | ψ_c | C25/30 | 1,02 | | | | | | | | | | |
| | | | C30/37 | 1,04 | | | | | | | | | | |
| | | | C35/45 | 1,07 | | | | | | | | | | |
| | | | C40/50 | 1,08 | | | | | | | | | | |
| | | | C45/55 | 1,09 | | | | | | | | | | |
| | | | C50/60 | 1,10 | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | | |
| Installation factor | | | | | | | | | | | | | | |
| dry or wet concrete | vacuum cleaning | | γ_{inst} | [-] | 1,2 | | | | | | | | | |
| | manual cleaning | | | | 1,2 | | | | | No performance assessed | | | | |
| | compressed air cleaning | | | | 1,0 | | | | | | | | | |
| waterfilled drill hole | compressed air cleaning | | γ_{inst} | [-] | 1,4 | | | | | | | | | |

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

Injection System VMH for concrete

Performance

Characteristic values of tension loads for rebar, 100 years working life

Annex C12

Table C14: Characteristic values of shear loads for rebar, static and quasi-static action

| Reinforcing bar | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | |
|---|-----------------------------|--------------------------------------|------|------|------|------|------|------|-------------------------|------|------|--|
| Steel failure <u>without</u> lever arm | | | | | | | | | | | | |
| Characteristic shear resistance | $V_{Rk,s}^0$ [kN] | $0,50 \cdot A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | |
| Cross sectional area | A_s [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | |
| Partial factor | $\gamma_{Ms,V}$ [-] | 1,5 ²⁾ | | | | | | | | | | |
| Ductility factor | k_7 [-] | 1,0 | | | | | | | | | | |
| Steel failure <u>with</u> lever arm | | | | | | | | | | | | |
| Characteristic bending resistance | $M_{Rk,s}^0$ [Nm] | $1,2 \cdot W_{el} \cdot f_{uk}^{1)}$ | | | | | | | | | | |
| Elastic section modulus | W_{el} [mm ³] | 50 | 98 | 170 | 269 | 402 | 785 | 1357 | 1534 | 2155 | 3217 | |
| Partial factor | $\gamma_{Ms,V}$ [-] | 1,5 ²⁾ | | | | | | | | | | |
| Concrete pry-out failure | | | | | | | | | | | | |
| Pry-out Factor | k_8 [-] | 2,0 | | | | | | | | | | |
| Concrete edge failure | | | | | | | | | | | | |
| Effective length of rebar | l_f [mm] | min (h_{ef} ; 12 d_{nom}) | | | | | | | min (h_{ef} ; 300mm) | | | |
| Outside diameter of rebar | d_{no_m} [mm] | 8 | 10 | 12 | 14 | 16 | 20 | 24 | 25 | 28 | 32 | |
| Installation factor | γ_{inst} [-] | 1,0 | | | | | | | | | | |

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

Injection System VMH for concrete

Performance
Characteristic values of **shear loads** for rebar

Annex C13

Table C15: Characteristic values of tension loads for rebar, seismic action
(performance category C1), 50 and 100 years working life

| Reinforcing bar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | |
|--|-------------------------|--------------------|-------------------------|------|------|------|------|------|------|------|------|------|-----|
| Steel failure | | | | | | | | | | | | | |
| Characteristic resistance | $N_{Rk,s,C1}$ | [kN] | $A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | |
| Cross sectional area | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | |
| Partial factor | $\gamma_{Ms,N}$ | [-] | 1,4 ²⁾ | | | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | |
| Characteristic bond resistance in concrete C20/25 to C50/60 | | | | | | | | | | | | | |
| Temperature range | I: 40°C / 24°C | $\tau_{Rk,C1}$ | [N/mm ²] | 5,5 | 5,5 | 6,0 | 6,5 | 6,5 | 6,5 | 6,5 | 7,0 | 7,0 | 7,0 |
| | II: 80°C / 50°C | | | 5,5 | 5,5 | 6,0 | 6,5 | 6,5 | 6,5 | 6,5 | 7,0 | 7,0 | 7,0 |
| | III: 120°C / 72°C | | | 4,5 | 5,0 | 5,0 | 5,5 | 5,5 | 5,5 | 5,5 | 6,0 | 6,0 | 6,0 |
| | VI: 160°C / 100°C | | | 4,0 | 4,5 | 4,5 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 |
| Installation factor | | | | | | | | | | | | | |
| dry or wet concrete | vacuum cleaning | γ_{inst} | [-] | 1,2 | | | | | | | | | |
| | compressed air cleaning | γ_{inst} | [-] | 1,0 | | | | | | | | | |
| waterfilled drill hole | | γ_{inst} | [-] | 1,4 | | | | | | | | | |

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

Table C16: Characteristic values of shear loads for rebar, seismic action (performance category C1)

| Reinforcing bar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 |
|---|-----------------|--------------------|------------------------------------|------|------|------|------|------|------|------|------|------|
| Steel failure <u>without</u> lever arm | | | | | | | | | | | | |
| Characteristic resistance | $V^0_{Rk,s,C1}$ | [kN] | $0,35 \cdot A_s \cdot f_{uk}^{1)}$ | | | | | | | | | |
| Cross sectional area | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 |
| Partial factor | $\gamma_{Ms,V}$ | [-] | 1,5 ²⁾ | | | | | | | | | |
| Ductility factor | k_7 | [-] | 1,0 | | | | | | | | | |

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

Injection System VMH for concrete

Performance
Characteristic values for rebar under seismic action

Annex C14

Table C17: Displacements under tension load (threaded rod)

| Threaded rod | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|---|----------------------------|-----------------------------|-----------------------------|-------|-------|-------|-------|-------|-------|-------|
| Displacement factor ¹⁾ uncracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | |
| Temperature range I: 40°C / 24°C | δ_{N0} -factor | [mm [N/mm ²] | 0,031 | 0,032 | 0,034 | 0,037 | 0,039 | 0,042 | 0,044 | 0,046 |
| | $\delta_{N\infty}$ -factor | | 0,040 | 0,042 | 0,044 | 0,047 | 0,051 | 0,054 | 0,057 | 0,060 |
| Temperature range III: 120°C / 72°C | δ_{N0} -factor | | 0,032 | 0,034 | 0,035 | 0,038 | 0,041 | 0,044 | 0,046 | 0,048 |
| | $\delta_{N\infty}$ -factor | | 0,042 | 0,044 | 0,045 | 0,049 | 0,053 | 0,056 | 0,059 | 0,062 |
| Temperature range VI: 160°C / 100°C | δ_{N0} -factor | | 0,121 | 0,126 | 0,131 | 0,142 | 0,153 | 0,163 | 0,171 | 0,179 |
| | $\delta_{N\infty}$ -factor | | 0,124 | 0,129 | 0,135 | 0,146 | 0,157 | 0,168 | 0,176 | 0,184 |
| Displacement factor ¹⁾ cracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | |
| Temperature range I: 40°C / 24°C | δ_{N0} -factor | | [mm [N/mm ²] | 0,081 | 0,083 | 0,085 | 0,090 | 0,095 | 0,099 | 0,103 |
| | $\delta_{N\infty}$ -factor | 0,104 | | 0,107 | 0,110 | 0,116 | 0,122 | 0,128 | 0,133 | 0,137 |
| Temperature range III: 120°C / 72°C | δ_{N0} -factor | 0,084 | | 0,086 | 0,088 | 0,093 | 0,098 | 0,103 | 0,107 | 0,110 |
| | $\delta_{N\infty}$ -factor | 0,108 | | 0,111 | 0,114 | 0,121 | 0,127 | 0,133 | 0,138 | 0,143 |
| Temperature range VI: 160°C / 100°C | δ_{N0} -factor | 0,312 | | 0,321 | 0,330 | 0,349 | 0,367 | 0,385 | 0,399 | 0,412 |
| | $\delta_{N\infty}$ -factor | 0,321 | | 0,330 | 0,340 | 0,358 | 0,377 | 0,396 | 0,410 | 0,424 |
| Displacement, seismic action (C2) | | | | | | | | | | |
| All temperature ranges | $\delta_{N,C2}$ (DLS) | [mm] | | -2) | 0,24 | 0,27 | 0,29 | 0,27 | -2) | |
| | $\delta_{N,C2}$ (ULS) | | 0,55 | | 0,51 | 0,50 | 0,58 | | | |

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau;$$

τ : acting bond stress for tension

$$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau;$$

²⁾ No performance assessed

Table C18: Displacements under shear load (threaded rod)

| Threaded rod | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|--|----------------------------|-----------|------|------|------|------|------|------|------|------|
| Displacement factor ¹⁾ cracked and uncracked concrete, static and quasi-static action | | | | | | | | | | |
| All temperature ranges | δ_{V0} -factor | [mm/(kN)] | 0,06 | 0,06 | 0,05 | 0,04 | 0,04 | 0,03 | 0,03 | 0,03 |
| | $\delta_{V\infty}$ -factor | | 0,09 | 0,08 | 0,08 | 0,06 | 0,06 | 0,05 | 0,05 | 0,05 |
| Displacement, seismic action (C2) | | | | | | | | | | |
| All temperature ranges | $\delta_{V,C2}$ (DLS) | [mm] | -2) | 3,6 | 3,0 | 3,1 | 3,5 | -2) | | |
| | $\delta_{V,C2}$ (ULS) | | | 7,0 | 6,6 | 7,0 | 9,3 | | | |

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V;$$

V: acting shear load

$$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V;$$

²⁾ No performance assessed

Injection System VMH for concrete

Performance
Displacements (threaded rod)

Annex C15

Table C19: Displacements under tension load (internally threaded anchor rod)

| Internally threaded anchor rod | | | VMU-IG M 6 | VMU-IG M 8 | VMU-IG M 10 | VMU-IG M 12 | VMU-IG M 16 | VMU-IG M 20 |
|--|----------------------------|----------------------------|---------------|---------------|----------------|----------------|----------------|----------------|
| Displacement factor¹⁾ uncracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | |
| Temperature range I: 40°C / 24°C | δ_{N0} -factor | mm [N/mm ²] | 0,032 | 0,034 | 0,037 | 0,039 | 0,042 | 0,046 |
| | $\delta_{N\infty}$ -factor | | 0,042 | 0,044 | 0,047 | 0,051 | 0,054 | 0,060 |
| Temperature range III: 120°C / 72°C | δ_{N0} -factor | | 0,034 | 0,035 | 0,038 | 0,041 | 0,044 | 0,048 |
| | $\delta_{N\infty}$ -factor | | 0,044 | 0,045 | 0,049 | 0,053 | 0,056 | 0,062 |
| Temperature range VI: 160°C / 100°C | δ_{N0} -factor | | 0,126 | 0,131 | 0,142 | 0,153 | 0,163 | 0,179 |
| | $\delta_{N\infty}$ -factor | | 0,129 | 0,135 | 0,146 | 0,157 | 0,168 | 0,184 |
| Displacement factor¹⁾ cracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | |
| Temperature range I: 40°C / 24°C | δ_{N0} -factor | mm [N/mm ²] | 0,083 | 0,085 | 0,090 | 0,095 | 0,099 | 0,106 |
| | $\delta_{N\infty}$ -factor | | 0,107 | 0,110 | 0,116 | 0,122 | 0,128 | 0,137 |
| Temperature range III: 120°C / 72°C | δ_{N0} -factor | | 0,086 | 0,088 | 0,093 | 0,098 | 0,103 | 0,110 |
| | $\delta_{N\infty}$ -factor | | 0,111 | 0,114 | 0,121 | 0,127 | 0,133 | 0,143 |
| Temperature range VI: 160°C / 100°C | δ_{N0} -factor | | 0,321 | 0,330 | 0,349 | 0,367 | 0,385 | 0,412 |
| | $\delta_{N\infty}$ -factor | | 0,330 | 0,340 | 0,358 | 0,377 | 0,396 | 0,424 |

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau; \quad \tau: \text{acting bond stress for tension}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau;$$

Table C20: Displacements under shear load (internally threaded anchor rod)

| Internally threaded anchor rod | | | VMU-IG M 6 | VMU-IG M 8 | VMU-IG M 10 | VMU-IG M 12 | VMU-IG M 16 | VMU-IG M 20 |
|---|----------------------------|-----------|---------------|---------------|----------------|----------------|----------------|----------------|
| Displacement factor¹⁾ cracked and uncracked concrete, static and quasi-static action | | | | | | | | |
| All temperature ranges | δ_{V0} -factor | [mm/(kN)] | 0,07 | 0,06 | 0,06 | 0,05 | 0,04 | 0,04 |
| | $\delta_{V\infty}$ -factor | | 0,10 | 0,09 | 0,08 | 0,08 | 0,06 | 0,06 |

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V; \quad V: \text{acting shear load}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V;$$

Injection System VMH for concrete

Performance
Displacements (internally threaded anchor rod)

Annex C16

Table C21: Displacements under tension load (rebar)

| Rebar | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | |
|--|----------------------------|----------------------------|----------------------------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| Displacement factor¹⁾ uncracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | | | |
| Temperature range I: 40°C / 24°C II: 80°C / 50°C | δ_{N0} -factor | mm [N/mm ²] | 0,031 | 0,032 | 0,034 | 0,035 | 0,037 | 0,039 | 0,042 | 0,043 | 0,045 | 0,048 |
| | $\delta_{N\infty}$ -factor | | 0,040 | 0,042 | 0,044 | 0,045 | 0,047 | 0,051 | 0,054 | 0,055 | 0,058 | 0,063 |
| Temperature range III: 120°C / 72°C | δ_{N0} -factor | | 0,032 | 0,034 | 0,035 | 0,036 | 0,038 | 0,041 | 0,044 | 0,045 | 0,047 | 0,050 |
| | $\delta_{N\infty}$ -factor | | 0,042 | 0,044 | 0,045 | 0,047 | 0,049 | 0,053 | 0,056 | 0,057 | 0,060 | 0,065 |
| Temperature range VI: 160°C / 100°C | δ_{N0} -factor | | 0,121 | 0,126 | 0,131 | 0,137 | 0,142 | 0,153 | 0,163 | 0,164 | 0,172 | 0,186 |
| | $\delta_{N\infty}$ -factor | | 0,124 | 0,129 | 0,135 | 0,141 | 0,146 | 0,157 | 0,168 | 0,169 | 0,177 | 0,192 |
| Displacement factor¹⁾ cracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | | | |
| Temperature range I: 40°C / 24°C II: 80°C / 50°C | δ_{N0} -factor | | mm [N/mm ²] | 0,081 | 0,083 | 0,085 | 0,087 | 0,090 | 0,095 | 0,099 | 0,099 | 0,103 |
| | $\delta_{N\infty}$ -factor | 0,104 | | 0,107 | 0,110 | 0,113 | 0,116 | 0,122 | 0,128 | 0,128 | 0,133 | 0,141 |
| Temperature range III: 120°C / 72°C | δ_{N0} -factor | 0,084 | | 0,086 | 0,088 | 0,090 | 0,093 | 0,098 | 0,103 | 0,103 | 0,107 | 0,113 |
| | $\delta_{N\infty}$ -factor | 0,108 | | 0,111 | 0,114 | 0,118 | 0,121 | 0,127 | 0,133 | 0,133 | 0,138 | 0,148 |
| Temperature range VI: 160°C / 100°C | δ_{N0} -factor | 0,312 | | 0,321 | 0,330 | 0,340 | 0,349 | 0,367 | 0,385 | 0,385 | 0,399 | 0,425 |
| | $\delta_{N\infty}$ -factor | 0,321 | | 0,330 | 0,340 | 0,349 | 0,358 | 0,377 | 0,396 | 0,396 | 0,410 | 0,449 |

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau; \quad \tau: \text{acting bond stress for tension}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau;$$

Table C22: Displacements under shear load (rebar)

| Rebar | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | |
|---|----------------------------|-----------|------|------|------|------|------|------|------|------|------|------|
| Displacement factor¹⁾ cracked and uncracked concrete, static and quasi-static action | | | | | | | | | | | | |
| All temperature ranges | δ_{V0} -factor | [mm/(kN)] | 0,06 | 0,05 | 0,05 | 0,04 | 0,04 | 0,04 | 0,03 | 0,03 | 0,03 | 0,03 |
| | $\delta_{V\infty}$ -factor | | 0,09 | 0,08 | 0,08 | 0,06 | 0,06 | 0,05 | 0,05 | 0,05 | 0,04 | 0,04 |

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V; \quad V: \text{acting shear load}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V;$$

Injection System VMH for concrete

Performance
Displacements (rebar)

Annex C17